



Licai Pigment

海宁市丽彩颜料化工有限公司
Haining Licai Pigment Chemical Co., Ltd.

中国海宁市海昌南路426号 P.C.Code: 314400

426 Haichangnan Road, Haining, China.

SOLVENT RED 26

Product name: Solvent red 26

Molecular formula: $C_{25}H_{22}N_4O$

CAS No.: 4477-79-6

Product specification

Appearance	Dark red powder
Tinting Strength	100±3%
Shade Color	Similar to the standard
Ash	≤ 1.0%
Moisture	≤ 1.0%
Color Differential Value ΔE	≤ 0.7

Commentary

Water insoluble dyes with high tinctorial strength, good solubility in most organic solvents, oil, fats and waxes.

Test Items	PS	ABS	SAN	PMMA	PC	R-PVC	PA6	PET
Heat resistance temperature, °C (0.05% dyes, transparent)	240	-	-	-	-	-	--	-
Heat resistance temperature, °C (0.05% dyes + 1.0% Titanium dioxide)	240	-	-	-	-	-	-	-
Migration resistance	-	-	-	-	-	-	-	-
Light fastness (0.05% dyes, transparent)	5-6	-	-	-	-	-	-	-
Weather resistance	-	-	-	-	-	-	-	-
Acid resistance (in 5% hydrochloric acid solution)	-	-	-	-	-	5	-	-
Alkali resistance (in 5% caustic soda solution)	-	-	-	-	-	5	-	-

Application Profile

PS	●	HIPS	○	ABS	○
PC	○	PVC-R	●	PMMA	○
SAN	○	Wax	●	Candle	●
Lubricating grease	●	Gasoline dyeing	●		

● = recommended ○ = potential use - = not recommended

Disclaimer

All above data are obtained by our best knowledge and regarded as references for you. We strongly recommended a trial test before your mass application.

TDS code: TDS-SR26-1