

海宁市丽彩颜料化工有限公司 Haining Licai Pigment Chemical Co., Ltd.

中国海宁市海昌南路426号 P.C.Code: 314400 426 Haichangnan Road, Haining, China.

Transparent Red TB

Color Index: Solvent red 146

Molecular formula:

CAS No.: 70956-30-8

Product specification

Appearance Dark red powder

Tinting Strength 100±3%

Shade Color Similar to the standard, red with blue shade

Ash ≤ 1.0% Moisture ≤ 0.5% Color Differential Value Δ E ≤ 0.7

Commentary

A red with blue shade, good lightfastness and excellent heat resistance.

Test Items	PS	ABS	SAN	РММА	PC	R-PVC	PA	PET
Heat resistance temperature, $^{\circ}$ C (0.05% dyes, transparent)	300	280	280	280	-	280	-	-
Heat resistance temperature, $^{\circ}$ C (0.05% dyes + 1.0% Titanium dioxide)	300	260	280	280	-	280	-	-
Migration resistance	-	-	-	-	-	-	-	-
Light fastness (0.05% dyes, transparent)	6-7	-	-	-	-	-	-	-
Weather resistance	-	-	-	-	-	-	-	-
Acid resistance (in 5% hydrochloric acid solution)	-	-	-	-	-	-	-	-
Alkali resistance (in 5% caustic soda solution)	-	-	-	-	-	-	-	-

Application Profile

PS	•	HIPS	0	ABS	0
PC	-	PVC-R	0	PMMA	0
SAN	0	AS	0	PA	-
PET	0				

• = recommended \circ = potential use - = not recommended

Disclaimer

All above data are obtained by our best knowledge and regarded as references for you. We strongly recommended a trial test before your mass application.

Technical Data Sheet TDS code: TDS-SR146-1