



Licai Pigment

海宁市丽彩颜料化工有限公司  
Haining Licai Pigment Chemical Co., Ltd.  
中国海宁市海昌南路426号 P.C.Code: 314400  
426 Haichangnan Road, Haining, China.

## Transparent Violet B

Color Index: Solvent Violet 13

Molecular formula:  $C_{21}H_{15}NO_3$

CAS No.: 81-48-1

IUPAC Name: l-hydroxy-4-[(4-methyl-phenyl)amino]

### Product specification

Appearance	Violet to blue powder
Tinting Strength	100±3%
Shade Color	Similar to the standard, violet with blue shade
Ash content	≤ 0.5%
Moisture	≤ 0.5%
Color Differential Value $\Delta E$	≤ 0.7

### Commentary

A blue shade violet with excellent lightfastness and good heat resistance.

Test Items	PS	ABS	SAN	PMMA	PC	R-PVC	PA6	PET
Heat resistance temperature, °C (0.05% dyes, transparent)	280	280	280	280	280	-	-	-
Heat resistance temperature, °C (0.05% dyes + 1.0% Titanium dioxide)	280	260	280	280	280	-	-	-
Migration resistance	-	-	-	-	-	-	-	-
Light fastness (0.05% dyes, transparent)	7-8	6	-	-	8	7-8	-	7-8
Weather resistance	-	-	-	-	-	-	-	-
Acid resistance (in 5% hydrochloric acid solution)	-	-	-	-	-	5	-	-
Alkali resistance (in 5% caustic soda solution)	-	-	-	-	-	5	-	-

### Application Profile

PS	●	HIPS	●	ABS	●
PC	●	PVC-R	●	PMMA	●
SAN	○	AS	○	PA	-
PET	●				

● = recommended ○ = potential use - = not recommended

### Disclaimer

All above data are obtained by our best knowledge and regarded as references for you. We strongly recommended a trial test before your mass application.

Technical Data Sheet

TDS code: TDS-SV13-1