



**海宁市丽彩颜料化工有限公司**  
**Haining Licai Pigment Chemical Co., Ltd.**  
 中国海宁市海昌南路426号 P.C.Code: 314400  
 426 Haichangnan Road, Haining, China.

## Technical data sheet

Product name: Solvent Violet 59  
 CAS No.: 6408-72-6

Molecular formula:  $C_{26}H_{18}N_2O_4$

### Product specification

Appearance	Violet powder
Tinting Strength	100 2%
Shade Color	Similar to the standard, violet with red shade
Ash	≤ 0.5%
Moisture	≤ 1.0%
Insolubles in xylene	≤ 0.5%
Color Differential Value $\Delta E$	≤ 0.7

### Commentary

A brilliant red violet hue with excellent lightfastness and good heat resistance. The chemistry is registered as solvent violet 59 and disperse violet 26.

Test Items	PS	ABS	SAN	PMMA	PC	R-PVC	PA6	PET
Heat resistance temperature, °C (0.05% dyes, transparent)	300	-	300	300	300	-	-	-
Heat resistance temperature, °C (0.05% dyes + 1.0% Titanium dioxide)	300	280	280	300	300	-	-	-
Migration resistance	-	-	-	-	-	-	-	-
Light fastness (0.05% dyes, transparent)	7-8	6	-	-	8	7	-	7
Weather resistance	-	-	-	-	-	-	-	-
Acid resistance (in 5% hydrochloric acid solution)	-	-	-	-	-	5	-	-
Alkali resistance (in 5% caustic soda solution)	-	-	-	-	-	5	-	-

### Application Profile

PS	●	HIPS	●	ABS	●
PC	○	PVC-R	●	PMMA	●
SAN	○	AS	●	PA	-
PET	○				

● = recommended ○ = potential use - = not recommend

### Disclaimer

All above data are obtained by our best knowledge and regarded as references for you. We strongly recommended a trial test before your mass application.

TDS code: TDS-SV59-1