

海宁市丽彩颜料化工有限公司 Haining Licai Pigment Chemical Co., Ltd.

中国海宁市海昌南路426号 P.C.Code: 314400 426 Haichangnan Road, Haining, China.

Transparent Blue 2B

Color Index: Solvent blue 104 Molecular formula: $C_{32}H_{30}N_2O_2$

CAS No.: 116-75-6

Product specification

Appearance Blue powder

Tinting Strength 100±3%

Shade Color Similar to the standard, blue

Ash ≤ 0.5% Moisture ≤ 0.5% Color Differential Value \triangle E ≤ 0.7

Commentary

A blue with high color strength, good lightfastness and good heat resistance.

Test Items	PS	ABS	SAN	PMMA	PC	R-PVC	PA6	PET
Heat resistance temperature, °C (0.05% dyes, transparent)	300	300	300	300	300	280	-	300
Heat resistance temperature, °C (0.05% dyes + 1.0% Titanium dioxide)	280	280	280	280	280	280	-	280
Migration resistance	-	-	-	-	-	-	-	-
Light fastness (0.05% dyes, transparent)	7-8	5	-	-	7-8	7	-	-
Weather resistance	-	-	-	-	-	-	-	-
Acid resistance (in 5% hydrochloric acid solution)	-	-	-	-	-	5	-	-
Alkali resistance (in 5% caustic soda solution)	-	-	-	-	-	5	-	-

Application Profile

PS	•	HIPS	•	ABS	•
PC	•	PVC-R	•	PMMA	•
SAN	•	AS	•	PA	-
PET	•				

• = recommended \circ = potential use - = not recommended

Disclaimer

All above data are obtained by our best knowledge and regarded as references for you. We strongly recommended a trial test before your mass application.

Technical Data Sheet TDS-SB104-1