

# 海宁市丽彩颜料化工有限公司 Haining Licai Pigment Chemical Co., Ltd.

中国海宁市海昌南路426号 P.C.Code: 314400 426 Haichangnan Road, Haining, China.

## **Transparent Black BN**

Color Index: Solvent Black 3 Molecular formula: C<sub>29</sub>H<sub>24</sub>N<sub>6</sub>

CAS No.: 4197-25-5

### **Product specification**

Appearance Black powder

Tinting Strength 100±3%

Shade Color Similar to the standard.

Ash  $\leq 0.5\%$  Moisture  $\leq 0.5\%$  Color Differential Value $\Delta$ E  $\leq 0.7$ 

#### Commentary

A black shade with good lightfastness and good heat resistance.

Test Items	PS	ABS	SAN	РММА	PC	R-PVC	PA6	PET
Heat resistance temperature, $^{\circ}$ C (0.05% dyes, transparent)	300	-	-	280	-	260	-	-
Heat resistance temperature, $^{\circ}$ C (0.05% dyes + 0.5% Titanium dioxide)	280	-	ı	260	-	260	-	-
Migration resistance	-	-	-	-	-	-	-	-
Light fastness (0.05% dyes, transparent)	7	-	-	-	-	-	-	-
Weather resistance	-	-	-	-	-	-	-	-
Acid resistance (in 5% hydrochloric acid solution)	-	-	-	-	-	5	-	-
Alkali resistance (in 5% caustic soda solution)	-	-	-	-	-	5	-	-

#### **Application Profile**

PS	•	HIPS	0	ABS	0
PC	0	PVC-R	•	PMMA	•
SAN	0	AS	0	PA	-
PET	0	Soap	•	Shoe polish	•

• = recommended  $\circ$  = potential use - = not recommended

#### Disclaimer

All above data are obtained by our best knowledge and regarded as references for you. We strongly recommended a trial test before your mass application.

Technical Data Sheet TDS code: TDS-SB3-1